

Product Technical Information Sheet

Blockleys™

Porcelain White Smooth

Configuration (EN 771.1):	Vertically Perforated Clay Facing Brick		Dimensions:	215 x 102.5 x 65 mm	
Compressive Strength:	>= 40	N/mm ²	Dimensional Tolerance:	T1	
Compressive Strength Category:	II		Dimensional Range:	R1	
Freeze/Thaw Resistance:	F2		Water Absorption:	=< 15	%
Soluble Salts Content Category:	S2		Initial Rate of Water Absorption:	1.8	kg/m ² .min
Reaction to Fire:	Class A1		Dangerous Substances:	N/A	
Thermal Conductivity (P = 50):	0.5	W/m.K	Thermal Resistance (P = 50):	0.21	m ² .K/W
Thermal Conductivity (P = 90):	0.56	W/m.K	Thermal Resistance (P = 90):	0.18	m ² .K/W
Void Percentage:	24 - 28	%	Net Dry Density:	1815	kg/m ³
Water Vapour Permeability Coefficient:	5/10		Gross Dry Density:	1300	kg/m ³
Bond Strength (fixed value):	0.15	N/mm ²	Density Tolerance:	D1	
Quantity per Pack:	432		Recycled Content:	44	%
Product Weight:	1.9	kg	DoP common root reference code:	KE030/01E	
Products per Square Metre:	60				

Clay bricks are manufactured and supplied to relevant clauses of **BS EN 771-1**.

Declarations of performance, environmental and other policies can be found on the company website: www.mbhplc.co.uk. Further information is available via our sales department on 0844 931 0022 or email sales@mbhplc.co.uk.

