

Product Technical Information Sheet

Carlton™

Red Dragwire

| | | | |
|--|--|-----------------------------------|-----------------------------------|
| Configuration (EN 771.1): | Vertically Perforated Clay Facing Brick | Dimensions: | 215 x 102.5 x 65 mm |
| Compressive Strength: | >= 40 N/mm ² | Dimensional Tolerance: | T2 |
| Compressive Strength Category: | II | Dimensional Range: | R1 |
| Freeze/Thaw Resistance: | F2 | Water Absorption: | =< 10 % |
| Soluble Salts Content Category: | S2 | Initial Rate of Water Absorption: | 1.5 kg/m ² .min |
| Reaction to Fire: | Class A1 | Dangerous Substances: | N/A |
| Thermal Conductivity (P = 50): | 0.62 W/m.K | Thermal Resistance (P = 50): | 0.17 m ² .K/W |
| Thermal Conductivity (P = 90): | 0.69 W/m.K | Thermal Resistance (P = 90): | 0.15 m ² .K/W |
| Void Percentage: | 26 - 30 % | Net Dry Density: | 2100 kg/m ³ |
| Water Vapour Permeability Coefficient: | 50/100 | Gross Dry Density: | 1500 kg/m ³ |
| Bond Strength (fixed value): | 0.15 N/mm ² | Density Tolerance: | D1 |
| Quantity per Pack: | 504 | Recycled Content: | 0 % |
| Product Weight: | 2.103 kg | DoP common root reference code: | --CT65FABR-- |
| Products per Square Metre: | 60 | | |

Clay bricks are manufactured and supplied to relevant clauses of **BS EN 771-1**.

Declarations of performance, environmental and other policies can be found on the company website: www.mbhplc.co.uk. Further information is available via our sales department on 0844 931 0022 or email sales@mbhplc.co.uk.

