



Hampshire Stock Downs Blend

TECHNICAL INFORMATION

Dimensional Tolerance:	T1
Dimensional Range:	R1
Durability against freeze/thaw:	F2
Active Soluble Salts Content Category:	S2
Gross Dry Density:	1400 kg/m ³
Compressive Strength:	6 N/mm ²
Water Absorption Shown:	18 %
Thermal Conductivity:	0.41 W/m.K-50% 0.47 W/m.K-90%
Dimensions:	215mm x 102.5mm x 65mm